

PRODUCT DATA SHEET

NORGLASS LABORATORIES PTY.LTD.
A.B.N. 92 001 807 245
P.O. Box 312, Neutral Bay. NSW 2089 Australia
59 Moxon Road, Punchbowl NSW
Ph: 61 2 9708 2200 Fax: 61 2 9796 3069
Email: norglass@bigpond.net.au
www.norglass.com.au

NORSHIELD ANTI-CORROSIVE PRIMER



DESCRIPTION: A dense red oxide, 2 pack epoxy primer for metal surfaces. Contains leafing pigments for excellent anti-corrosive performance..

USES: As a primer for ferrous metals and many other substrates. Can be used on areas of continuous immersion as well as high rise structures.

PROPERTIES (at 20°C)

COLOUR: Red oxide

TOXICITY: See Precautions

FINISH: Low to semi-gloss

COVERAGE: to 10sq.metres/mixed litre (subject to porosity and/or texture)

DRYING TIME: Touch dry in 2 hours

RECOATING: Spraying – wet on wet. Brush/roller – overnight

POT LIFE: 8 hours

MIXING RATIO: 3 parts base to 1 part hardener by volume

THINNING: Spraying – 25% - 33 $\frac{1}{3}$ % Northane Spraying Thinners, depending on pressure system used.
Brush/roller – 5% Norglass Epoxy Thinner

WEIGHT/LITRE: 6.25kg when mixed

VOLUME SOLIDS: 50%

FLASH POINT: 27°C (SOLVENT)

CLEAN UP: Norglass Epoxy Thinners or Northane Spraying Thinner

UN NUMBER: 1263

- STEEL:** Sandblast to white metal (AS 1627.4) or power sand to a clean metal state.
- OTHER METALS:** Sandblast or solvent degrease and sand to a clean metal state
- OTHER SURFACES:** Ensure the surface is clean, dry, sanded and well prepared.
- APPLICATION:** Mix 3 parts of Norshield Base with 1 part Norshield Hardener by volume, stir thoroughly and allow to stand for a further 10 minutes before using. Apply by brush roller, airless or conventional spray.
Adjust Spraying Thinners according to the pressure system used or thin 25-33% at 50-70 psi.
- TRANSPORTATION:** Dangerous Goods Class 3.2 HAZCHEM 3[Y]PGIII
Pack sizes available – 4litre, 1litre, 500ml
- PRECAUTIONS:** This product is Polyamide cured and all precautions must be observed.
Read labels carefully.
The hardener is alkaline and should be treated with care as it can cause skin irritations.
If spraying, provide adequate ventilation as the vapours may be harmful.
Do not smoke during use and keep away from naked flame.
- FIRST AID:** If poisoning occurs call a doctor or Poisons Information Centre (Aust) on 13 11 26 or (NZ) 0800 764 766 and have label information ready.
If swallowed DO NOT induce vomiting. Give large quantities of water or milk. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and consult a doctor. Remove contact lenses if present and easy to do and continue rinsing. In case of skin contact, remove contaminated clothing and wash skin thoroughly. If breathing difficulty arises remove to fresh air. Apply artificial respiration if not breathing.
- SPECIAL INSTRUCTIONS:** Avoid using this product below 10degreesC because curing will be affected.
Where only a portion of the hardener is used, reseal the container immediately, as the product deteriorates rapidly on exposure to air.
NOTE: If remaining contents are not used within 48 hours of opening, decant into a small clean container to reduce the air space and seal tightly.