

PRODUCT DATA SHEET

NORGLASS LABORATORIES PTY.LTD. A.B.N. 92 001 807 245 P.O. Box 312, Neutral Bay. NSW 2089 Australia 59 Moxon Road, Punchbowl NSW Ph: 61 2 9708 2200 Fax: 61 2 9796 3069 Email: norglass@bigpond.net.au www.norglass.com.au



NORSYSTEM BOAT EPOXY RESIN (FAST HARDENER)

 DESCRIPTION:
 A fast setting Hardener for colder climates.

 USES:
 Laminating timbers with composite reinforcing materials gluing, filling and fairing.

PROPERTIES (at 20°C)

COLOUR:	Clear when mixed with Norsystem Base
TOXICITY:	See precautions
FINISH:	Clear
COVERAGE:	Varies according to uses
CURE TO SOLID:	6-8 Hours. When mixed with Norsystem Base
POT LIFE @22°C FOR 100MLS:	20-25 minutes (when mixed)
MIXING RATIO:	1:3 by volume
THINNING:	Not recommended
WEIGHT/LITRE:	1.012
VOLUME SOLIDS:	100%
FLASH POINT:	> 100°C
CLEAN UP:	Norglass Epoxy Thinner
U.N. NUMBER:	2735
PREPARATION:	Refer to NORGLASS REINFORCING GUIDE for use.

APPLICATION:	Varies according to methods used. Mixing ratio is 3 parts by volume of Norsystem Base with 1 part by volume of Norsystem Slow or Fast Hardener. Thorough stirring is essential . Allow 5-10 minutes for induction then add the extenders selected or pour into a shallow paint tray for laminating. Apply by squeegee, spatula or short nap roller for the chosen application.
TRANSPORTATION:	Hazchem Code: N/A. Dangerous goods class: Not applicable. Sizes: 1.5 Litre, 750 ml, 250 ml
PRECAUTIONS:	Mild skin irritant. Some allergic reactions can occur. If this happens, cease using immediately . Wear protective clothing at all times. Provide adequate ventilation during use.
FIRST AID:	If poisoning occurs call a doctor or Poisons Information Centre (Aust) on 13 11 26 or (NZ) 0800 764 766 and have label information ready. If swallowed DO NOT induce vomiting. Give large quantities of water or milk. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and consult a doctor. Remove contact lenses if present and easy to do and continue rinsing. In case skin contact causes irritation, remove contaminated clothing and wash skin thoroughly. If breathing difficulty arises remove to fresh air. Apply artificial respiration if not breathing.
SPECIAL INSTRUCTIONS:	Crush empty containers and send to landfill. Liquid residue to be mixed with sand before going to land fill.